



AeroShell Grease 22

AeroShell Grease 22 is a versatile advanced general purpose grease composed of a synthetic hydrocarbon oil thickened with Microgel®, with outstanding performance characteristics. Appropriate additives are included to achieve the necessary oxidation and corrosion resistance, anti-wear properties and load carrying properties. The useful operating temperature range is -54°C to $+177^{\circ}\text{C}$.

DESIGNED TO MEET CHALLENGES

Main Applications

- AeroShell Grease 22 is especially recommended for use wherever severe operating conditions are encountered as in high bearing loads, high speeds, wide operating temperature range, and particularly where long grease retention and high resistance to water washout are required.
- The wide range of applications include aircraft wheel bearings, engine accessories, control systems, actuators, screw-jacks, servo mechanisms and electric motors, helicopter rotor bearings, instruments, airframe lubrication, hinge pins, static joints, landing gears.
- AeroShell Grease 22 contains a synthetic hydrocarbon oil and should not be used in contact with incompatible seal materials.

Specifications, Approvals & Recommendations

- U.S. : Approved MIL-PRF-81322G NLGI Grade 2, Approved DOD-G-24508A
- British : Approved DEF STAN 91-52
- French : Approved DCSEA 395/A
- Russian : Analogue of CIATIM 201 and 203, VNII NP 207, ERA (VNII NP 286M) and ST (NK-50)
- NATO Code : G-395
- Joint Service Designation : XG-293
- COMAC Approved to QPL-CMS-OL-301

For a full listing of equipment approvals and recommendations, please consult your local Shell Technical Helpdesk.

Typical Physical Characteristics

Properties	Method	MIL-PRF-81322G	Typical
Oil type		-	Synthetic Hydrocarbon
Thickener type		-	Microgel
Base Oil viscosity @-40°C	mm ² /s	-	7500
Base Oil viscosity @40°C	mm ² /s	-	30.5
Base Oil viscosity @100°C	mm ² /s	-	5.7
Useful operating temperature range	°C	-	-54 to +177
Dropping point	°C	ASTM D2265	232 minimum
Worked penetration @25°C		ASTM D217	256 to 320
Bomb Oxidation pressure drop 100 hrs @99°C	kPa	ASTM D942	83 maximum
Bomb Oxidation pressure drop 500 hrs @99°C	kPa	ASTM D942	172 maximum
Oil separation 30 hrs @177°C	% m	ASTM D6184	2.0 to 8.0
Water washout @41°C	% m	ASTM D1264	20 maximum
Evaporation loss 22 hrs @177°C	% m	ASTM D2595	10 maximum
Anti-friction bearing performance @177°C	hrs	ASTM D3336	400 minimum

Properties	Method	MIL-PRF-81322G	Typical
Load carrying capacity . kg	ASTM D2596	30 minimum	40
Copper corrosion 24 hrs @100°C	ASTM D4048 FED-STD-791 5309	Must pass	Passes
Colour	Visual	-	Amber

These characteristics are typical of current production. Whilst future production will conform to Shell's specification, variations in these characteristics may occur.

Health, Safety & Environment

- **Health and Safety**

Guidance on Health and Safety is available on the appropriate Safety Data Sheet, which can be obtained from <http://www.epc.shell.com/>

- **Protect the Environment**

Take used oil to an authorised collection point. Do not discharge into drains, soil or water.

Additional Information

- **Advice**

Advice on applications not covered here may be obtained from your Shell representative.