



BONDERITE C-MC 80

Known as P3-grato 80 March 2019

PRODUCT DESCRIPTION

BONDERITE C-MC 80 provides the following product characteristics:

Technology	Industrial Cleaner	
Product Type	Alkaline Cleaner	
Application	General Cleanin	g,
	Maintenance cleaning	
Concentration	depends on requirements	
Operating Temperature	room temperature up to 100 °C	

BONDERITE C-MC 80 is an alkaline cleaner for steel and non-ferrous metals. It is composed of alkalis, silicates, phosphonates, anionic and non-ionic surfactants. Light metals should be checked before use.

Application Areas:

BONDERITE C-MC 80 is a highly efficient high-pressure and steam cleaner.

TECHNICAL DATA

Appearance clear, yellow brownish

liquid

Density at 20°C, ~1.16 g/cm³

DIN 51757

pH-value (20% solution): ~12.2

DIRECTIONS FOR USE

Preliminary Statement:

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Bath Make-up:

BONDERITE C-MC 80 is used as delivered or in dilution (up to 1:10) depending on the application.

Concentration 5 to 20 g/L for high pressure at nozzle exit

Concentrated contaminants:

pre-cleaning / high pressure treatment

Wet the surface with the concentrated product.

The mobilized soil is removed by spraying with high pressure (water or diluted cleaner solution, 5 to 10 g/L).

Light contaminants:

direct high pressure treatment

Dilute the cleaner solution (50 to 100 g/L). Apply directly into the high pressure unit.

Manual cleaning

The surface is cleaned with diluted BONDERITE C-MC 80 solution (5 to 100 g/L).

Post treatment

Drying without separate rinsing prevents flash rust formation. For follow-up treatment the remaining film can be rinsed off with water.

Operating Data:

Temperature room temperature

up to 100 °C

Duration of treatment: depends on requirements

Spray pressure 10 to 100 bar

Bath Control:

BONDERITE C-MC 80 solution is controlled by the following analysis.

Feed, mL 100 mL

Titrant: 0.5 N hydrochloric acid Indicator: phenolphthaleine (0.1% alcoholic solution)

Titration factor (TF): 2.2

- Pipette 100 mL bath solution into a clean 300 mL Erlenmeyer-flask.
- Add 3 to 5 drops of indicator.
- Titrate the solution with 0.5 N hydrochloric acid.
- The endpoint will be shown by a colour change from pink to colourless (pH-value: 8.2).
- The added mL of 0.5 N hydrochloric acid multiplied by the factor TF 2.2 is equal to the concentration in g/L.
- Divide this by 10 to get the value in %.

Classification:

Please refer to the corresponding **Material Safety Data Sheets** for details on:

Hazards identification Transport information Regulatory information



Storage:

Recommended Storage Temperature Shelf-life, months

0 to 45°C 24 months

ADDITIONAL INFORMATION

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0