

BONDERITE L-GP D 148A ACHESON

Known as ENDU PTFE D 148A
June 2015

PRODUCT DESCRIPTION

BONDERITE L-GP D 148A ACHESON provides the following product characteristics:

Technology	Lubricant
Product Type	PTFE dispersion in solvent
Application	Dry film lubricant

BONDERITE L-GP D 148A ACHESON is a PTFE based varnish developing a dry and lubricating coating after curing. BONDERITE L-GP D 148A ACHESON forms a smooth and dry lubricant film.

BONDERITE L-GP D 148A ACHESON is a 2 compounds material used in combination with a hardener (BONDERITE S-OT DURCISSEUR/ BONDERITE S-OT AH 1 ACHESON).

TECHNICAL DATA

(of wet product)

Aspect	Viscous green liquid
Solids content, %	51 to 53
Viscosity, mPa.s (Brookfield 20 °C, 20 rpm)	100 to 200
Flash Point, °C	-4
Density, kg/m ³	1,280

DIRECTION OF USE

Preliminary Statement

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Method of Use

- BONDERITE L-GP D 148A ACHESON resin compound is used in combination with BONDERITE S-OT AH 1 ACHESON.
- Homogenize BONDERITE L-GP D 148A ACHESON.
- The BONDERITE S-OT AH 1 ACHESON is added to the to the BONDERITE L-GP D 148A ACHESON, while stirring.
- The mixing ratio is: 100 grams of BONDERITE L-GP D 148A ACHESON with 17 grams of BONDERITE S-OT AH 1 ACHESON.
- Stir the blend correctly to full homogeneity.
- The pot life of the blend is 20 hours at 20 °C.

Pretreatment

The surfaces have to be clean and well degreased. A sand-blasting of the surface improves the adhesion of the film.

Application

The blend of resin and hardener is adjusted to the correct viscosity for spray using thinner.

Curing

About 24 hours at room temperature.

The hardening can be accelerated by heat: after 1 hour air drying, the heat hardening sequences are:

- cure during 2 hours at 60 °C
- cure during 1 hour at 150 °C
- cure during 30 minutes at 180 °C

Thinners

- Ethylacetate, MEK, MIBK
- Never use alcohols

Storage

Recommended Storage Temperature, °C	5 to 40
Shelf life, months (in unopened original packaging)	12

Classification

Please refer to the corresponding **Material Safety Data**

Sheets for details on:

- Hazards identification**
- Transport information**
- Regulatory information**

ADDITIONAL INFORMATION

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0