



BOSTIK 1782 (CLEAR)

SOLVENT BASED ADHESIVE

KEY FEATURES

- Good chemical & temperature resistance
- Bonds many substrates
- Colourless in a dry film

DESCRIPTION

Bostik 1782 is a general purpose adhesive, the dried film of which is virtually colourless and non-staining. **Bostik 1782** is of medium viscosity and provides a strong bond which has good chemical and temperature resistance and excellent ageing properties.

RECOMMENDED USE

Bostik 1782 has many industrial uses and is particularly suitable for bonding leather, metals, wood, canvas, PVC and other plastics. It is widely used in the manufacture of toys, leather goods, furniture, upholstery, jewellery, many kinds of plastic-ware, etc.

The UK Ministry of Defence quality assurance and release document relating to **Bostik 1782** is AFS 265D - **this specification does not apply to material supplied in tubes**

NOTE: To obtain enhanced bond properties with better resistance to high temperatures, oil, petrol and kerosene **Bostik 1782** may be used in conjunction with **Bostikure D curing agent** as a two part, cold curing adhesive system.

IMPORTANT

Before embarking on any work involving **Bostik 1782** the safety data sheet should be carefully studied by those carrying out the work.

BSI STANDARDS



METHOD OF USE

SURFACE PREPARATION

- Surfaces must be dry, clean and grease free. If they are non-porous, smooth or glossy, they may be cleaned by abrading the surface with clean emery cloth or by using **Bostik cleaner 7**
- Rubber surfaces should be abraded, as the use of solvents for cleaning these does not give entirely satisfactory results.
- Thick plastic sheets should be abraded.
- Porous surfaces may not need cleaning, but must be dry, grease free and firm.

ADHESIVE PREPARATION

When using as a two part system with **Bostikure D** the mix ratio is 100 parts of adhesive to 6 parts of **Bostikure D** (by weight) or by taking:

Bostik 1782

1 litre tin
5 litre tin

Bostikure D

D40 bottle
D200 bottle

The pot life of the mixed adhesive in a closed container is approximately 8 hours at normal room temperatures.

APPLICATION TECHNIQUES

Brush - The adhesive must be applied evenly to the surface being coated.

Spraying - Dilute with **cleaner 7** or **cleaner 6** for application by suitable spray equipment. This equipment must be thoroughly cleaned at the end of the day.

Roller coating - **Bostik 1782** can be used in some roller coaters, but in general it is necessary to dilute with **cleaner 7** or **cleaner 6**

Knife blade spreader - **Bostik 1782** can be used as supplied in certain types of knife blade spreaders.

On some porous surfaces, a single application may be insufficient and a multi-coat application technique should be used. Intermediate coats should be allowed to dry for about 30 minutes, but the final coat should have the normal 5 to 10 minutes drying time.

BONDING METHODS

Five bonding methods may be used

Two way dry stick

- Apply an even film of the adhesive to both surfaces by one of the techniques detailed under "application techniques".
- Allow the two films to dry for 5 to 10 minutes or until they can be touched with the knuckles without any adhesive being transferred.
- Join the surfaces, taking care not to trap any air and using as much pressure as possible.

One way wet stick

- Apply the adhesive to one surface only and bond immediately using as much pressure as possible.
- This will give a lower initial bond strength than the two way dry stick, maximum bond strength being attained in 3 to 7 days. T
- This technique can only be used where one or both surfaces to be joined are porous.

One way semi-wet stick

- For use with very thin plastic sheeting that is curled by the action of the adhesive.
- Apply the adhesive to the surface to which the sheet will be bonded and allow to dry for approximately 4 minutes.
- The plastic sheeting is then rolled on to the semi-wet surface, using as much pressure as possible.

Heat Activation

- Apply the adhesive to both surfaces and allow to dry completely.
- The coated surfaces may be left for several days providing they are kept clean and dry.
- Either heat both surfaces to 100°C and bond together immediately under pressure, or place the joined surfaces in a heated press at 100°C for 1 to 2 minutes.

Solvent Activation

- Apply the adhesive to both surfaces and allow to dry completely.
- The coated surfaces may be left for several days providing they are kept clean and dry.
- Activate both surfaces by brushing or spraying with **cleaner 7**.
- Allow approximately 30 seconds for solvent evaporation and then bond under pressure

TYPICAL CHARACTERISTICS	
Physical form	Mobile liquid
Colour	Colourless
Chemical type	Nitrile rubber/resin solution
Odour	Ketonic
Solvent	Mixture of Ketones
Flash Point (closed cup)	In the group -18°C to -7°C
Flammability	Highly Flammable
Viscosity, Brookfield RVT, 10rpm at 25°C	[mPa.s] Approx. 10000 in tins Approx. 3300 in tubes
Solids content	[%] Approx. 30 in tins Approx. 25 in tubes
Relative density	Approx. 0.9
Coverage	Approx. 2.8m ² per litre (1.4m ² per litre bonded area) but can vary with material being bonded
Temperature resistance	-40 to +80°C (-40 to +100°C when cured with Bostikure D)
Water resistance	Good
Oil, petrol & kerosene resistance	Good, but will not withstand prolonged immersion. (Very good when cured with Bostikure D)
Solvent resistance	Good to intermittent contact with alcohols. Not resistant to ketones & esters
Dilute acid & alkali resistance	Good
Cleaner	Use cleaner 7 for surface cleaning, the removal of surplus adhesive and for cleaning application equipment

PACKAGING

Please refer to Customer Service Department for current pack sizes.

STORAGE

Store in original sealed containers in a dry, well ventilated, flameproof place between 5 – 25°C.

SHELF LIFE

At least 12 months from date of manufacture, under the above conditions of storage.

Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products..

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, or its liability for fraud, or fraudulent misrepresentation, or any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number on the bottom right hand side of this page.

SMART HELP

Please contact your local representative

