

2402 ADHESIVE

POLYCHLOROPRENE ADHESIVE

BOSTIK 2402 ADHESIVE is a solvent-borne formulation based on polychloroprene rubber. It is used in conjunction with BOSTIKURE D CURING AGENT* as a TWO PART, cold curing adhesive system which has a wide range of industrial applications. It gives strong resilient bonds which exhibit good resistance to water, heat, humidity, etc.

* See Information Sheet No. B596.

RECOMMENDED USE

BOSTIK 2402 ADHESIVE will bond natural, polychloroprene, nitrile, butyl, Hypalon and polyurethane rubber surfaces, rigid PVC, wood, metal, leather, etc. It can be used as a heat-resistant adhesive for decorative laminated plastics, and is particularly useful in the construction of inflatable products such as boats, balloons, etc.

BOSTIK 2402 ADHESIVE is approved, in conjunction with BOSTIK 9252 PRIMER, under the UK Ministry of Defence Specification DTD900/4679A for bonding synthetic rubber de-icer shoes to aircraft propeller blades and for use in the manufacture and repair of aircrew and survival clothing and of inflatable equipment. For these and other appropriate general purpose applications the quality assurance and release document approved by the UK Ministry of Defence is AFS 1179B.

IMPORTANT: It is not recommended that BOSTIK 2402 ADHESIVE be used on plasticised PVC because of the possibility of plasticiser migration.

BONDING INSTRUCTIONS

1. The surfaces to be bonded must be dry, clean and grease-free. To ensure correct surface preparation remove any grease present by wiping with a clean cloth wetted with BOSTIK CLEANER/THINNER M501. Then abrade the surface with clean emery cloth and remove the ensuing dust by wiping with another clean cloth moistened with BOSTIK CLEANER/THINNER M501.

When bonding certain materials, such as wood and decorative laminates, it is not normally necessary to abrade them but they must be dry, clean and grease-free. If necessary remove any surface contamination with BOSTIK CLEANER/THINNER M501.

2. Stir the BOSTIK 2402 thoroughly for a few minutes, to ensure any ingredients which may have settled in storage are thoroughly redispersed. Ensure there is no solid sediment on the bottom of the container before proceeding.
3. Mix together thoroughly, for approximately 5 minutes, BOSTIK 2402 ADHESIVE and BOSTIKURE D CURING AGENT, preferably in the proportions as supplied or by taking (by weight) 100 parts of the adhesive and 6 parts of the curing agent.

Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, or its liability for fraud, or fraudulent misrepresentation, or any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

4. Apply an even coat of the mixed adhesive to both mating surfaces by brush, roller coater or serrated trowel.
5. Allow the adhesive coats to dry for 10 to 20 minutes or until they can just be touched with the knuckles without any adhesive being transferred.

NOTE: Two thin coats are preferable for maximum adhesion. The first coat should be allowed to dry for approximately 20 to 30 minutes before applying the final coat and allowing this to dry for 10 to 20 minutes.

6. Join the surfaces, taking care not to trap any air, using as much pressure as possible. Components may be handled within minutes of being bonded.

For the strongest adhesion to metal use BOSTIK 9252 PRIMER, full details of which are given in Information Sheet No.B67. Stir this primer thoroughly and then apply by brush an even, thin coat to the prepared metal surfaces. Allow the primer coat to dry for at least one hour before applying BOSTIK 2402 ADHESIVE.

PRECAUTIONS MUST BE TAKEN TO ENSURE THAT BOSTIK 2402 ADHESIVE, BOSTIKURE D CURING AGENT AND THE MIXED UNCURED ADHESIVE ARE NOT CONTAMINATED WITH WATER OR WATER VAPOUR, AS THIS COULD HAVE A DETRIMENTAL EFFECT ON BOND STRENGTHS.

Tack Life:	Approximately 20 to 30 minutes dependent on the surfaces being bonded.
Pot Life:	6 to 8 hours in a closed container, but shorter in open containers due to solvent evaporation. Also the pot life decreases with age of the adhesive.
Curing Time:	48 hours under normal ambient temperature conditions but the strength of the adhesive bond continues to increase, reaching its maximum within 7 days. Cure rate may be accelerated by heating e.g. 2 hours at approximately 70°C.
Coverage:	Approximately 4m ² per litre but can vary with material being bonded. (2m ² bonded area).
Cleaner/Thinner:	BOSTIK CLEANER/THINNER M501 is suitable for cleaning surfaces but may attack painted surfaces . Use BOSTIK CLEANER/THINNER M501 for adhesive dilution, removal of surplus adhesive and cleaning of application tools and equipment.

TYPICAL CHARACTERISTICS

Physical Form:	Semi-viscous liquid
Colour:	Off white
Odour:	Sweet
Chemical Type:	Polychloroprene rubber/resin based solution
Solvent:	Mixture of toluene, light petroleum spirit, acetone and butanone

Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, or its liability for fraud, or fraudulent misrepresentation, or any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Viscosity:	Approximately 2.5 Pa s (25 poise) at 25°C
Solids Content:	Approximately 22%
Specific Gravity:	Approximately 0.9
Flammability:	Highly flammable
Flash Point (Closed Cup)	In the group -18 to -7°C
Temperature Resistance:	From -40 to +90°C but will withstand higher temperatures for short periods.
Water Resistance:	Good
Oil, Petrol & Kerosene Resistance:	Fair – good.
Solvent Resistance:	Not resistant to esters, ketones, aromatic and chlorinated hydrocarbons which may swell and soften the bond.
Acid & Alkali Resistance:	Good. Virtually unaffected by 5N sulphuric acid and 5N sodium hydroxide
Humidity Resistance:	Good, after exposure to 100% RH at 38°C for 14 days
Ageing:	Good but exposed adhesive film will darken.

PACKAGING

Please refer to Customer Service Department for details of current pack sizes.

STORAGE

Store in a dry flameproof area between 5 and 25°C.

SHELF LIFE

12 months from date of manufacture, under the above conditions of storage.

MATERIAL SAFETY DATA

For further information refer to the relevant Health and Safety Data Sheet.

Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, or its liability for fraud, or fraudulent misrepresentation, or any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.