

Technical Data Sheet

BETAPRIME 5500

Description / Application:

Sprayable "one-step" primer for glass and ceramic substrates used in combination with all Betaseal Polyurethane adhesive sealants.

All Dow Automotive products are primarily developed in co-ordination with the automobile manufacturers, according to their needs and their specifications; they are approved for the specific applications as defined by the customer.

The use of the product other than approved application have to be released in writing by the Technical Service of Dow Automotive.

Technical Data:

Basis Polyisocyanates

Colour Black

Pigments Carbon black

Density 0.953+/-0.02 g/cm³ at 23°C

Viscosity (DIN-cup 4) < 14 s at 23°C

Flash point -6°C
Processing temperature 10 - 40°C

Evaporation time Min: from approx. 30 s at 23°C/50% rh if sprayed and after

approx. 3 Min. using felt. The film should be touch-free.

Max: 3 d at 23°C/50% r.h.

Instructions for use Shake container well before opening. Continue to shake for

at least 60 s after steel balls inside the container are

released.

Caution! The product is extremely hygroscopic! Close containers immediately to preserve remaining contents. Use

up remainder within two days.

Bonding surface preparation The surface has to be free of impurities. We recommend pilot

tests

Processing equipment Primer application, primer application unit (with primer

application head and felt), primer sprayer.

Cleaning Clean equipment with BETACLEAN 3000

Shelf life 6 months at +5 - +25°C in unopened containers (see "use

before" date printed on container)

Containers

Aluminium containers: 250 ml; upon request other sizes also

available.

Protection measures

See health and safety data sheet.

Dow Automotive Quality Management

Quality is our highest priority. Dow Automotive works with a highly modern Quality Management System which meets all international requirements of **QS 9000, VDA-6** and **ISO 9001**.

Dow Automotive AG

CH-8807 Freienbach Tel. +41(0)55416 81 11 Fax +41(0)55416 82 20

Dow Automotive (Deutschland) GmbH

D-35683 Dillenburg Tel. +49(0)2771 8 71 40 Fax +49(0)2771 87 14 70

Dow Automotive (Italia) S.r.l

I-20010 Bareggio (MI) Tel. +39(0)2 90 36 11 66 Fax +39(0)2 90 27 66 98

Dow Automotive (España) S.A.

E-28816 Camarma de Esteruelas (Madrid) Tel. +34 (9)1 886 61 43 Fax +34 (9)1 885 75 60

Dow Automotive (France) S.A.

F-60130 Saint-Just en chaussee Tel. +33(0) 3 44 77 61 00 Fax. +33(0) 3 44 77 61 61

Dow Automotive (UK) Ltd.

GB-Nuneaton-Warwickshire CV10 7QT

Tel. +44 (0) 24 7635 72 00 Fax. +44 (0) 24 7635 72 57