

UVCL

UV Cure Conformal Coating

DESCRIPTION

UVCL is a low viscosity, single-part conformal coating, which cures rapidly on exposure to the correct dose of UV light. **UVCL** has a highly effective, moisture initiated secondary cure mechanism to ensure curing in shadowed areas. It has been specifically designed to offer the highest level of protection for electronic circuitry at high production throughputs. **UVCL** has been designed for application via selective spray equipment and demonstrates ease of automation, along with excellent storage stability and shelf-life.

READ ENTIRE TECHNICAL BULLETIN BEFORE USING THIS PRODUCT

FEATURES AND BENEFITS

- Dual cure system; secondary moisture cure for full cure, even in shadow areas
- Eliminates the use of solvents; VOC-free and non-flammable coating
- No dilution required; low viscosity, ready to use for selective spray application
- Ultimate protection in harsh environments, including high humidity, corrosive and chemical atmospheres

APPROVALS

Standard	Status
RoHS Compliant (2015/863/EU)	Yes
IPC-CC-830	Meets Requirements
IEC-61086	Meets Requirements
UL Approval	UL746-QMJU2 (File: E138403)

PRODUCT INFORMATION

For available packaging sizes please visit:

electrolube.com

PHYSICAL PROPERTIES

Category	Results
Liquid Properties	
Appearance	Pale Color Liquid
Base Material	Urethane Acrylate
Density @ 20 °C (g/mL)	1.1
VOC Content	0%
Flash Point (°C)	>90
Solid Content	100%
Viscosity (mPa s @ 25 °C)	225 to 400
Coverage @ 100 µm	10 m ² /L
Dry Film Coating	
Color	Colorless
Operating Temperature Range (°C)	-65 to 135
Flammability	UL94 V-0
Dielectric Strength (kV/mm)	27
Dielectric Constant @ 1MHz	2.5
Surface Insulation Resistance	1 x 10 ¹⁵ Ω
Dissipation Factor @ 1MHz, 25 °C	0.01
Moisture Resistance (IPC-CC-830)	7 x 10 ¹² Ω
Thermal Shock IPC-CC-830 (-65 to 125 °C) Additional (-40 to 125 °C)	Pass 100 Cycles Pass > 100 Cycles
Glass Transition Temperature (°C)	7
Tensile Strength (MPa @ 20 °C) (BS EN ISO 537)	2.7
Elastic Modulus (MPa) (BS EN ISO 537)	

Category	Results
-40°C	2940
25°C	2.2
130°C	2.2
Elongation at Break (BS EN ISO 537)	100%

APPLICATION GUIDELINES

Substrates should be thoroughly cleaned before coating to ensure satisfactory adhesion to the substrate. All flux residues should be removed as they may become corrosive or interfere with adhesion if left on the PCB. Electrolube manufacture a range of cleaning products using both hydrocarbon solvent and aqueous technology.

UVCL has been specifically designed for automated processes using selective spray technology however other spraying techniques and touch-up application via brush may also be employed. The coating application must be done away from the UV light source to prevent premature curing.

APPLICATION GUIDELINES – RESIN PACKS

Spraying – Bulk

UVCL is supplied at a viscosity suitable for selective spraying. Due to the secondary moisture curing capability of the product, it is advised that all storage tanks are kept sealed to protect from moisture, thereby ensuring product quality. Fluid transfer lines, nozzles and applicator heads should all be immersed in Industrial Machine Cleaner (IMC) when not in use.

A range of application thicknesses are possible with UVCL, depending on the spray equipment and parameters employed. Suitable coating thickness should be determined by the user, for each application, ensuring the required levels of protection for the PCB are met. However, typical thicknesses of 100 to 200µm are regularly used within the industry, providing high levels of resistance to moisture, chemicals and debris, whilst possessing a good balance between surface hardness and bulk flexibility.

TYPICAL PRODUCT APPLICATION

Brushing

As it is a manual process with many variables, brush coating is only advised for touch-up applications. Brushes should be clean and dry prior to use and exposure to UV light minimized to avoid premature curing.

Curing

The speed of UV cure depends on a number of factors, namely the wavelength, the intensity and the dosage of UV light used for curing, the applied coating thickness and the height of the components on the PCB. Once UVCL has been exposed to the recommended UV curing regime (detailed overleaf), a fully touch dry coating that is suitable for downstream processing will be obtained. Shadow areas, not exposed to UV light, are cured via a secondary moisture cure mechanism. The time for full cure of the whole coating therefore also depends on the environmental conditions of humidity and temperature.

For effective UV curing of UVCL, Electrolube recommend the use of standard mercury bulbs ('H' type) with typical conveyor speeds in the region of 1.0-1.5m/min. The minimum and maximum values for intensity (peak irradiance) and dosage (energy density) that should be used are as follows.

UV Lamp Outputs	Dosage (Energy Density), mJ/cm ²				Intensity (Peak Irradiance), mW/cm ²			
	UVA	UVB	UVC	UVV	UVA	UVB	UVC	UVV
Wavelength Range								
Minimum	1800	1500	400	1500	350	300	90	275
Maximum	2800	2500	600	2500	500	400	110	375

All values measured using an EIT 'Power Puck II' radiometer.

It is essential that the correct wavelength, intensity and dosage of UV light is determined for each application on a case by case basis, prior to commencement of production runs using UVCL. Appropriate process parameters for effective curing should be established at implementation of any UV curing system and monitored regularly to ensure continued compliance to those parameters. A portable, calibrated radiometer should be used for this purpose.

Further information is available on request.

INSPECTION

UVCL contains a fluorescent dye, which allows 'blacklight' inspection of the PCB after coating, to ensure complete and uniform coverage. The stronger the reflected UV light, the thicker the coating layer is. UV light in the region of 375nm should be used for inspection.

ADDITIONAL INFORMATION

Shelf Life

Description	Shelf Life
UVCL UV Cure Coating	12 Months
Industrial Machine Cleaner	36 Months

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

CONTACT INFORMATION

To confirm this document is the most recent version, please contact
TechnicalSupportTeam@hkw.co.uk
www.electrolube.com

North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.367.5460	Europe Ashby Park Coalfield Way Ashby de la Zouch Leicestershire, LE65 1JR, UK 44.01530.41960	Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100
--	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE . Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.