

# LOCTITE<sup>®</sup> 4014™

September 2020

## PRODUCT DESCRIPTION

LOCTITE<sup>®</sup> 4014™ provides the following product characteristics:

<b>Technology</b>	Cyanoacrylate
Appearance (uncured)	Transparent, colorless to slightly yellow liquid <sup>LMS</sup>
Components	One part - requires no mixing
Viscosity	Very low
<b>Cure</b>	Humidity
<b>Application</b>	Bonding
Key Substrates	Plastics and Metals

LOCTITE<sup>®</sup> 4014™ is designed to provide fast room temperature fixturing and is also suitable for applications where heat resistance is required. Suitable for use in the assembly of **disposable medical devices**.

### ISO-10993

LOCTITE<sup>®</sup> 4014™ has been tested to Henkel's test protocols based on ISO 10993 biocompatibility standards, as a means to assist in the selection of products for use in the medical device industry.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.1
Flash Point - See SDS	
Viscosity, Cone & Plate, mPa·s (cP):	
Temperature: 25 °C, Shear Rate: 100 s <sup>-1</sup>	1 to 4 <sup>LMS</sup>
Viscosity, Brookfield - LVF, 25 °C, mPa·s (cP):	
Spindle 1, speed 30 rpm	1 to 5

## TYPICAL CURING PERFORMANCE

Under normal conditions, the atmospheric moisture initiates the curing process. Although full functional strength is developed in a relatively short time, curing continues for at least 24 hours before full chemical/solvent resistance is developed.

### Cure Speed vs. Substrate

The rate of cure will depend on the substrate used.

Fixture Time, seconds:	
PVC to PVC	60 to 80
ABS to ABS	5 to 10
Polycarbonate to Polycarbonate	20 to 25
Polyurethane to Polyurethane	8 to 10
G-10 Epoxy to G-10 Epoxy	25 to 30
Stainless steel to PVC	5 to 10
Stainless steel to ABS	5 to 10
Stainless steel to Polycarbonate	5 to 8
Stainless steel to Polyurethane	20 to 25
Stainless steel to G-10 Epoxy	6 to 10

### Cure Speed vs. Bond Gap & Humidity

The rate of cure will depend on the bondline gap. Thin bond lines result in high cure speeds, increasing the bond gap will decrease the rate of cure. The rate of cure is also influenced by the ambient relative humidity; the higher the relative humidity, the greater the cure speed.

### Cure Speed vs. Activator

Where cure speed is unacceptably long due to large gaps, applying activator to the surface will improve cure speed. However, this can reduce ultimate strength of the bond and therefore testing is recommended to confirm effect.

## TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 24 hours @ 22 °C

### Physical Properties:

Shore Hardness, ISO 868	65
Elongation, ISO 527-2, %	2
Tensile Strength, ISO 527-3	28 (4,000)

## TYPICAL PERFORMANCE OF CURED MATERIAL

### Adhesive Properties

Cured for 10seconds @ 22 °C

Tensile Strength, ISO 6922:

Buna-N	N/mm <sup>2</sup>	≥6.9 <sup>LMS</sup>
	(psi)	(≥1,000)

Cured for 24 hours @ 22 °C

Lap Shear Strength, :

PVC to PVC	N/mm <sup>2</sup>	>7.5
	(psi)	(>1,100)
ABS to ABS	N/mm <sup>2</sup>	>4
	(psi)	(>580)
Polycarbonate to Polycarbonate	N/mm <sup>2</sup>	>7.5
	(psi)	(>1,100)
Stainless steel to ABS	N/mm <sup>2</sup>	>5.5
	(psi)	(>800)
Stainless steel to PVC	N/mm <sup>2</sup>	>4
	(psi)	(>580)
Stainless steel to Polycarbonate	N/mm <sup>2</sup>	>4
	(psi)	(>580)
Stainless steel to Polyurethane	N/mm <sup>2</sup>	1.5
	(psi)	(220)

Cured for 24 hours @ 22 °C, followed by 24 hours @ 121 °C, tested @ 22 °C

Lap Shear Strength, :

Steel (grit blasted)	N/mm <sup>2</sup>	≥12 <sup>LMS</sup>
	(psi)	(≥1,740)

## TYPICAL ENVIRONMENTAL RESISTANCE

### Humidity Resistance

38°C - 85% Relative Humidity

#### Adhesive Properties

Lap Shear Strength, N/mm<sup>2</sup> :

Substrates	1*	2*	3*	4*
PVC to PVC	>8	>5	>5	>5
ABS to ABS	>4	>3.5	>3	>2.5
Polycarbonate to polycarbonate	>8	>6.5	>6	>5.5
Stainless Steel to PVC	>6	>6	>5.5	>5.5
Stainless Steel to ABS	>4	>4	>5	>4
Stainless Steel to Polycarbonate	>4	>4	>4	>2
Stainless Steel to Polyurethane	1.5	1.4	2.2	2.0

\* 1 - Control

\* 2 - Aged 1 Week

\* 3 - Aged 4 weeks

\* 4 - Aged 8 weeks

### Effects of Sterilization

In general, products similar in composition to LOCTITE® 4014™ subjected to standard sterilization methods, such as EtO and Gamma Radiation (25 to 50 kiloGrays cumulative) show excellent bond strength retention. LOCTITE® 4014™ maintains bond strength after 1 cycle of steam autoclave. It is recommended that customers test specific parts after subjecting them to the preferred sterilization method. Consult with Loctite® for a product recommendation if your device will see more than 3 sterilization cycles.

### GENERAL INFORMATION

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

#### Directions For Use:

1. For best performance bond surfaces should be clean and free from grease.
2. This product performs best in thin bond gaps (0.05 mm).
3. Excess adhesive can be dissolved with Loctite cleanup solvents, nitromethane or acetone.

#### Loctite Material Specification<sup>LMS</sup>

LMS dated October 11, 2002. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

### Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 2 °C to 8 °C. Storage below 2 °C or greater than 8 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

### Conversions

(°C x 1.8) + 32 = °F

kV/mm x 25.4 = V/mil

mm / 25.4 = inches

µm / 25.4 = mil

N x 0.225 = lb

N/mm x 5.71 = lb/in

N/mm<sup>2</sup> x 145 = psi

MPa x 145 = psi

N·m x 8.851 = lb·in

N·m x 0.738 = lb·ft

N·mm x 0.142 = oz·in

mPa·s = cP

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of

any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.4