

LOCTITE ABLESTIK 50262-3

December 2016

PRODUCT DESCRIPTION

LOCTITE ABLESTIK 50262-3 provides the following product characteristics:

Technology	Epoxy
Appearance	Silver
Product Benefits	<ul style="list-style-type: none"> • One component • Electrically conductive • Low temperature cure • Low extractable ionics • Long pot life
Cure	Heat Cure
Application	Assembly
Typical Assembly Applications	Heat sensitive components

LOCTITE ABLESTIK 50262-3 can be applied by automatic syringe dispensing or by stencil printing. LOCTITE ABLESTIK 50262-3 adhesive is designed for applications where conventional solder is impractical.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield # TC, 25 °C, mPa·s (cP):

Speed 10 rpm	180,000
Density, g/cm ³	3.33
Fineness, μm	25
Pot Life @ 18 to 25°C, days	7
Shelf Life @ -25 to -18°C, days	182
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

Convection Oven

45 minutes @ 100°C or
25 minutes @ 120°C or
10 minutes @ 150°C or

IR Oven

3 to 4 minutes @ 120°C

Low temperature cure will reduce electrical conductivity.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties :

Coefficient of Linear Thermal Expansion, ppm/°C	60
Glass Transition Temperature (T _g), °C	90
Thermal Conductivity ASTM D1674, W/(m-K)	2
Extractable Ionic Content, ppm:	
Chloride (Cl ⁻)	10
Sodium (Na ⁺)	10
Potassium (K ⁺)	10
Ammonium (NH ₄ ⁺)	30

Electrical Properties:

Volume Resistivity, Ω·cm	5×10 ⁻³
--------------------------	--------------------

TYPICAL PERFORMANCE OF CURED MATERIAL

Tensile Lap Shear Strength :

N/mm ²	5
(psi)	(725)

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

THAWING:

1. This adhesive is packed and shipped in dry ice.
2. Transfer the syringes from the shipping container to a <0°C freezer without ANY delays.
3. Allow material to reach room temperature before use.

DIRECTIONS FOR USE

1. Refrigerate LOCTITE ABLESTIK 50262-3 to maintain viscosity.
2. Packages removed from storage must be allowed to return to ambient temperature before use. This normally takes 2 to 4hours for a 10 to 30 cc syringe.
3. LOCTITE ABLESTIK 50262-3 can be applied by syringe dispensing or stencil printing.
4. Equipment parts can be cleaned using solvents such as acetone, methyl ethyl ketone, ethanol, isopropanol or LOCTITE STYCAST CLEANER 50306.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : -25 to -18 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions $(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$ $\text{kV/mm} \times 25.4 = \text{V/mil}$ $\text{mm} / 25.4 = \text{inches}$ $\text{N} \times 0.225 = \text{lb}$ $\text{N/mm} \times 5.71 = \text{lb/in}$ $\text{psi} \times 145 = \text{N/mm}^2$ $\text{MPa} = \text{N/mm}^2$ $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$ $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$ $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$ $\text{mPa}\cdot\text{s} = \text{cP}$ **Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 1

Americas
+1.888.943.6535

Europe
+32.1457.5611

Asia
+86.21.3898.4800

For the most direct access to local sales and technical support visit: www.henkel.com/electronics