

LOCTITE EDAG 7019 E&C

November 2022

PRODUCT DESCRIPTION

LOCTITE EDAG 7019 E&C provides the following product characteristics:

Technology	Thermoplastic
Appearance	Grey Paste
Filler Type	Silver, Silver chloride
Silver : Silver chloride Ratio	8 : 2
Product Benefits	<ul style="list-style-type: none"> • Flexible • Good adhesion • Low electrical resistance • No thinning required • Long screen residence time • Ease of use
Cure	Heat Drying
Application	ECG Electrodes, Bio Medical Sensor
Typical Substrates	Treated and Untreated Polyester

LOCTITE EDAG 7019 E&C is a blend of finely divided silver and silver chloride particles in a thermoplastic resin. It is formulated to provide excellent adhesion to the wide variety of substrates used in the manufacture of electrically conductive medical devices.

TYPICAL PROPERTIES OF UNDRIED MATERIAL

Solids Content by Weight, %	63.3
Viscosity, Brookfield - RVT @ 30°C, mPa·s (cP):	
Spindle 6, speed 20 rpm	14,000
Density, kg/L	2.2
Shelf Life @ 2 to 8°C (from date of manufacture), days	365
Theoretical coverage @ 10 µm dry film thickness, m ² /kg	14
Flash Point, °C	93

TYPICAL DRYING PERFORMANCE
TYPICAL SCREEN PRINTING PROCESS

Screen Mesh, mesh/inch:	
Polyester with solvent-resistant emulsion	230 to 325
Recommended dry film thickness	5 to 14

TYPICAL DRYING CYCLE

VOC, g/L	700
Recommended Drying Cycle, @ 110°C, minutes	10

The above profiles are guideline recommendations. These conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer drying equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF DRIED MATERIAL
Physical Properties

Adhesion on PET, Cross Hatch, ASTM 3359, grade	5B
--	----

Electrical Properties

Sheet Resistance Ohm/sq/25µm	<0.05
------------------------------	-------

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

1. Contact with metal equipment and exposure to light should be avoided as much as possible due to product's silver chloride content.
2. Surface to be coated must be dry and free of contaminants such as oil or chemical residues.
3. LOCTITE EDAG 7019 E&C is supplied ready for use and does not require dilution.
4. Avoid rapid stirring as this causes air entrapment.
5. Should thinning become necessary, use dibastic ester (DBE) solvent (1 to 2% by weight).
6. The equipment can be cleaned with esters (butylacetate, propylacetate, orethylacetate) or ketones (MEK, Acetone).

CLEAN-UP

The equipment can be cleaned with esters (butylacetate, propylacetate, orethylacetate) or ketones (MEK, Acetone).

STORAGE

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 2 to 8 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb/F}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{N/mm}^2 = \text{MPa}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. © denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 4