

LOCTITE® PC 7352

April 2021

PRODUCT DESCRIPTION

LOCTITE® PC 7352 provides the following product characteristics:

Technology	Polyurea
Chemical Type	Polyurea
Appearance (resin)	Black liquid
Appearance (hardener)	Opaque straw yellow liquid
Appearance (mixed)	Black paste
Components	Two components – resin & hardener
Mix Ratio, by weight - Resin : Hardener	100 : 56
Application Temperature	10°C to 30°C (50°F to 86°F)
Mix Ratio, by volume - Resin : Hardener	100 : 50
Cure	Room temperature cure after mixing
Application	Rubber repairs
Specific Benefits	<ul style="list-style-type: none"> • Resurfacing and repairing of worn or damaged rubber parts • Flexible • Fast curing • Application on vertical position • High abrasion resistance

LOCTITE® PC 7352 is a 100% solid, room temperature curing, two component Polyurea compound. When cured it is a tough and resilient adhesive. This product offers an excellent balance of thixotropic behavior and fast cure. Its fast cure is specially designed for on-site repairs. Typical applications include repair and rebuild conveyor belts and liners in mills, pumps, feeder bowls, hoppers, and chutes.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Resin:

Specific Gravity @ 23 °C	1.08
Viscosity, Brookfield - RVT, 25°C, mPa·s (cP): Spindle 7, speed 20 rpm	61,000

Hardener:

Specific Gravity @ 23 °C	1.2
Viscosity, Brookfield - RVT, 25°C, mPa·s (cP): Spindle 7, speed 20 rpm	6,700

Mixed Properties:

Specific Gravity @ 23 °C	1.12
--------------------------	------


TYPICAL CURING PERFORMANCE

Cured @ 23°C, 50% RH

Gel Time, ASTM D2471, minutes	18
-------------------------------	----

Cure Speed vs. Temperature

The graph below shows the shear strength developed with time @ 23°C on grit blasted mild steel lap shears and tested according to ISO 4587.



TYPICAL PERFORMANCE OF CURED MATERIAL

Cured for 1 week @ 23°C

Physical Properties

Shore Hardness, ISO 868, Durometer A	51
Elongation, ISO 37, %	375
Tensile Strength, ISO 37	N/mm ² 14.3 (psi) (2,100)
Tensile Modulus, ISO 37	N/mm ² 1.5 (psi) (220)
Tear Strength, ISO 34-1, Type 1 Specimens	N/mm ² 18.2 (psi) (2,600)

Abrasion Properties

Taber Abrasion Resistance, ASTM D4060	
1 kg load, H-18 wheels, 1,000 cycles	mg 220
Weight of material lost (dry)	
1 kg load, CS 10 wheels, 1,000 cycles	mg 15
Weight of material lost (dry)	

Adhesive Properties

Lap Shear Strength, ISO 4587	
Grit Blasted Mild Steel	N/mm ² 3.5 (psi) (500)
Nitrile Rubber with Etching	N/mm ² 1.5 (psi) (220)
Neoprene with Etching	N/mm ² 0.5 (psi) (73)



TYPICAL ENVIRONMENTAL RESISTANCE

Chemical/Solvent Resistance

Cured for 1 week @ 23°C

Tables below show chemical resistance @ 23°C. Tested on product specimens, immersed up to 5,000 hours @ 23 °C in fluids indicated.

Acids

36 % Hydrochloric Acid	Spill, splash
10 % Nitric Acid	Spill, splash
5 % Phosphoric Acid	Continuous long term immersion
10 % Sulfuric Acid	Continuous long term immersion

Alkalis

25 % Ammonium Hydroxide	Short term or intermittent immersion
36 % Ammonium Sulphate	Continuous long term immersion

Solvents

100 % Deionized Water	Continuous long term immersion
10 % Salt Water	Continuous long term immersion
100 % MEK	Spill, splash

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Surface Preparation

Proper surface preparation is critical to the long-term performance of this product. The exact requirements vary with the severity of the application, expected service life, and initial substrate conditions

1. Cut away loose and damaged pieces of the rubber to be repaired.
2. Remove dirt, oil, grease, etc. from rubber with a suitable cleaner, e.g. TEROSON® VR 40 or TERSON® VR 10.
3. Abrade the repair area with an abrasive wheel or wire wheel to roughen the bond surface. Avoid overheating and melting the rubber during grinding.
4. Aggressively clean the prepared surfaces with LOCTITE® solvent based cleaner (i.e. TEROSON® VR 40 or TERSON® VR 10) and allow to dry.
5. Apply LOCTITE® Etching agent on clean rubber surface with a brush.
6. Let it act for 30 minutes at 25°C or 60 minutes at 10°C.

Application

1. Insert the cartridge into the application gun and push the plunger into the cylinders using light pressure on the trigger. Then, remove the cartridge cap and expel a small amount of adhesive to be sure both sides are flowing evenly and freely. Cut a piece of the static mixing nozzle to facilitate product flow. Attach the static mixing nozzle to the end of the cartridge.
2. Purge and dispose of the first 3 to 5 cm from the end

of the mix nozzle, as it may not be sufficiently mixed. Work quickly as material will begin to cure in static mixer.

3. Work the adhesive onto the substrate with a spatula to allow maximum surface contact and adhesion.
4. It is not necessary to use all the adhesive in the cartridge in one application. Leave the static mixer on the cartridge when application is complete. The mixer serves as a seal and should be discarded and replaced with a fresh mixer for the next application.

Color

1. Color variation is possible between the batches and will not affect the performance of the product.

Clean-up

1. Immediately after use clean tools with a Loctite® solvent base cleaner. Once cured, the material can only be removed mechanically..

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 5 to 35 °C. Storage below 0 °C or greater than 40 °C can adversely affect product properties. Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Product Specification

The technical data contained herein are intended as reference only and are not considered specifications for the product. Product specifications are located on the Certificate of Analysis. Please contact a Henkel representative for more information.

Approval and Certificate

Please contact a Henkel representative for related approval or certificate of this product.

Data Ranges

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23 °C / 50% RH = 23±2 °C / 50±5% RH

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$



Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0

