

# 4123 Epoxy Primer 7835

## TECHNICAL DATA SHEET

### Product Description

4123/.... is a two component chromated epoxy primer, used for external of aircraft structures.

- Anti corrosive primer
- Corrosion resistant
- Flexible
- Excellent resistance to oil esters, grease, kerosene, hydraulic fluids
- Heat resistant to temperatures up to 130 °C (266 °F)

### Components



#### Mix Ratio (by volume)

- |                         |   |
|-------------------------|---|
| • 4123/.... (Base)      | 1 part  |
| • 0628/9001 (Activator) | 1 part  |
| • 0469/9000 (Thinner)   | to viscosity (see viscosity section of this document) |

### Specifications



4123 is qualified to:

- DHS 186-111

4123 meets the technical requirements of:

- MIL-P-23377

#### Product Compatibility

4123 is compatible with the following topcoat specifications:

- |                  |                  |
|------------------|------------------|
| • AIMS 04-04-003 | • ECS 2139-20    |
| • AIMS 04-04-012 | • ECS-L-12261    |
| • ASNA 4247      | • NORMDEF 0003-1 |
| • BLGG 140301    |                  |

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

# 4123 Epoxy Primer 7835

## Surface Preparation and Pretreatment



Ensure surface to be painted is clean, dry and intact using a high performance solvent cleaner DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended.

## Instructions for Use



Ensure all mixing / measuring containers are free from contaminants. Shake or stir the base to ensure all components are adequately dispersed. Slowly add activator to base while stirring. Add required thinner to viscosity.

*Note: All products and components should be placed in ambient conditions of 15-30 °C (59-86 °F) for at least 24 hours prior to mixing and application.*



### **Induction Time:**


Not required



### **Viscosity:** ( 23 °C/73 °F)

• AFNOR 2.5	45 - 55 seconds
• AFNOR4	15 - 16 seconds
• BSB3	26 - 29 seconds
• BSB4	15 - 17 seconds
• FORD4	12 - 14 seconds
• ISO3	37 - 49 seconds
• ISO4	18 - 21 seconds
• ZAHN2	16 - 19 seconds

*Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.*



### **Pot Life:**

8 hours @ 21 - 25 °C (70 - 77 °F)

## Application Guidelines

### **Recommended Application Conditions:**

Temperature	15 - 30 °C (59 - 86 °F)
Relative Humidity	30 - 80%

# 4123 Epoxy Primer 7835

**Application:**


Apply 1 cross coat to achieve the recommended dry film thickness.



**Theoretical Coverage:** (ready for use)  
12 m<sup>2</sup>/Lt @ 25 µm dry film thickness  
480 ft<sup>2</sup>/US gal @ 1 mil dry film thickness

**Recommended Dry Film Thickness:**

20 - 25 µm  
0.8 - 1 mil



**Dry Film Density:**  
2.0 g/cm<sup>3</sup>  
16.6 lbs/US gal

**Dry Film Weight:**

48 g/m<sup>2</sup> @ 25 µm dry film thickness  
0.009 lbs/ft<sup>2</sup> @ 1 mil dry film thickness

*Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*

**Equipment:** 4123 is compatible with all current forms of spray equipment



Equipment Type	Tip Size	Pressure
Conventional Airspray	15/10 mm	43 to 72 psi (3 to 5 bar)
Airless	0.33 mm (angle 67 or 80°)	1450 to 1885 psi (100 to 130 bar)

**Equipment Cleaning:**

Clean spray equipment before use and as soon as possible after use. DeSoto<sup>®</sup> CN20 or Desoclean<sup>™</sup> 45 solvent cleaners are recommended.

**Physical Properties**



**Colour:**  
Green-Blue-Grey (4123/5045)  
Yellow-Green (4123/3600)

# 4123 Epoxy Primer 7835




**Gloss:**

Matt < 5 units with a 60° gloss meter



Drying Times @ 50 % R.H.	23°C (73°F)	60°C (140°F)	80°C(176°F)	120°C(248°F)
Dry to Touch	15 to 30 minutes			
Dry to Handle	1 to 1.5 hours			
Dry to Overcoat	4 hours (min.) 72 hours (max.)	20 minutes		
Dry to Tape	2 to 3 hours			
Full Cure	7 days		1 hour	15 minutes

*Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.*



**Flash Off:**

30 minutes prior to overcoating or force drying



**VOC: (ASTM)**

Mixed ready for use (unthinned)	600 g/Lt
4123 Base	460 g/Lt
0628/9001 Activator	750 g/Lt
0469/9000 Thinner	850 g/Lt



**Flash Point:**

4123 Base	15°C (59°F)
0628/9001 Activator	14°C (57°F)
0469/9000 Thinner	24°C (75°F)

**Shelf Life:**

4123 Base	24 months in original unopened container
0628/9001 Activator	24 months in original unopened container
0469/9000 Thinner	10 years in original unopened container

*Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.*

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

## 4123 Epoxy Primer 7835

### Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*



# 4123 Epoxy Primer 7835

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

#### **ASC – Australia**

Tel 61 (3) 9335 1557

Fax 61 (3) 9335 3490

#### **ASC – Japan**

Tel 81 561 35 5200

Fax 81 561 35 5201

#### **ASC – South East Asia**

Tel 65 6861 1119

Fax 65 6861 6162

#### **ASC – Suzhou**

Tel (86-512) 6661 5858

Fax (86-512) 6661 6868

#### **ASC – Tianjin**

Tel (86-022) 2482 8625

Fax (86-022) 2482 8600

### **Europe and Middle East**

#### **ASC – Central Europe**

Tel 49 (40) 742 193 10

Fax 49 (40) 742 139 69

#### **ASC – Middle East & India**

Tel (971) 4 883 9666

Fax (971) 4 883 9665

#### **ASC – North Europe**

Tel 44 (0) 1388 770222

Fax 44 (0) 1388 770288

#### **ASC – South Europe**

Tel 33 (0) 235 53 43 71

Fax 33 (0) 235 53 54 44

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

**Desoclean and DeSoto are trademarks of PRC-DeSoto International, Inc.**

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PPG Aerospace  
Sealants and Coatings  
Darlington Road  
Shildon, Co Durham UK  
DL4 2QP

[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 07/14

Lit:4227