

# CV121 Polyurethane Finishing Gloss

## TECHNICAL DATA SHEET

### Product Description

CV121 is a two part polyurethane based blue-tinted varnish designed for use on external surfaces of fuel tanks to prevent vapour fuel leakages and accumulation of fuel vapour in fuselage covered areas surrounding fuel tanks.

- Excellent flexibility
- Applicable on aluminium & carbon fibre composite
- Excellent resistance to water & hydraulic fluids

### Components



#### **Mix Ratio (by volume)**

- |                     |              |
|---------------------|--------------|
| • CV121 (Base)      | 2 parts      |
| • ACT34 (Activator) | 1 part       |
| • T74 (Thinner)     | to viscosity |

### Specifications



CV121 is qualified to:

- AIMS 04-04-008

CV121 is compatible with the following primer specifications:

- AIMS 04-04-001
- AIMS 04-04-002

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

### Surface Preparation and Pretreatment



Ensure surface is clean, dry and intact using a high performance solvent cleaner - DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended. Observe recommended overcoating windows.

# CV121 Polyurethane Finishing Gloss

## Instructions for Use



Stir or shake the base component to ensure complete dispersion. Add activator to base component and stir thoroughly. Add thinner to viscosity for spray application, no thinner is required for brush application.


*Note: All products and components should be placed in ambient conditions of 15-30 °C (59-86 °F) for at least 24 hours prior to mixing and application.*



### **Viscosity:** ( 23°C/73°F)

• AFNOR2.5	45 - 56 seconds
• AFNOR4	15 - 16 seconds
• BSB3	26 - 30 seconds
• BSB4	15 - 17 seconds
• FORD4	12 - 15 seconds
• ISO3	37 - 50 seconds
• ISO4	18 - 22 seconds
• ZAHN2	16 - 20 seconds

*Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.*



### **Pot Life:**

8 hours @ 21 - 25°C (70 - 77°F)

## Application Guidelines

### **Recommended Application Conditions:**

Temperature	15 - 30°C (59 - 86°F)
Relative Humidity	30 - 75%

### **Application:**

Apply 1 double track coat to achieve recommended dry film thickness.




### **Theoretical Coverage:** (ready for use)

11 - 15 m<sup>2</sup>/Lt @ 20 µm dry film thickness  
 440 - 600 ft<sup>2</sup>/US gal @ 0.8 mil dry film thickness

### **Recommended Dry Film Thickness:**

18 - 28 µm  
 0.7 - 1.1 (mil)

# CV121 Polyurethane Finishing Gloss



**Dry Film Density:** (unthinned)

1.08 g/cm<sup>3</sup>  
9.09 lbs/US gal

**Dry Film Weight:**

22 g/m<sup>2</sup> @ 20 μm dry film thickness  
0.004 lbs/ft<sup>2</sup> @ 0.8 mil dry film thickness

*Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*

**Equipment:**

CV121 is compatible with all current types of spray equipment or can be brush applied.



Equipment Type	Tip Size	Pressure
Airmix	9 to 11 thou	Refer to manufacturer
HVLP Air Spray	1.3 to 1.8 mm	29 to 43 psi (2 to 3 bar)
Pressure Pot	1.0 to 1.2 mm	29 to 43 psi (2 to 3 bar)
Airless	9 to 11 thou	Refer to manufacturer
Air-assisted Airless Electrostatic	9 to 11 thou	Refer to manufacturer
Low Pressure Electrostatic	1.0 to 1.2 mm	87 psi (6 bar)

**Equipment Cleaning:**

Clean spray equipment before use and as soon as possible after use. DeSoto<sup>®</sup> CN20 or Desoclean<sup>™</sup> 45 solvent cleaners are recommended.

**Physical Properties**



**Colour:**  
Transparent blue




**Gloss:**  
Full gloss

# CV121 Polyurethane Finishing Gloss



DRYING TIMES@ 23°C (73°F) 50% RH	
Dry to Handle	6 hours
Dry to Mask	6 hours
Dry to Recoat	2 - 72 hours
Dry to Flat	6 hours
Fully Cure	7 days

*Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.*



### Flash Off Time:

Not required



### VOC: (ASTM)

Mixed (unthinned)	455g/Lt
CV121 Base Component	550g/Lt
ACT34 Activator	270g/Lt
T74 Thinner	800g/Lt



### Flash Point:

CV121 Base Component	13°C (19°F)
ACT34 Activator	25°C (68°F)
T74 Thinner	-7°C (19°F)

### Shelf Life:

CV121 Base Component	24 months in original unopened container
ACT34 Activator	24 months in original unopened container
T74 Thinner	24 months in original unopened container

*Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.*

*Note: The application and performance property values are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

## Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*



# CV121 Polyurethane Finishing Gloss

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

#### **ASC – Australia**

Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

#### **ASC – Japan**

Tel 81 561 35 5200  
Fax 81 561 35 5201

#### **ASC – South East Asia**

Tel 65 6861 1119  
Fax 65 6861 6162

#### **ASC – Suzhou**

Tel (86-512) 6661 5858  
Fax (86-512) 6661 6868

#### **ASC – Tianjin**

Tel (86-022) 2482 8625  
Fax (86-022) 2482 8600

### **Europe and Middle East**

#### **ASC – Central Europe**

Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

#### **ASC – Middle East & India**

Tel (971) 4 883 9666  
Fax (971) 4 883 9665

#### **ASC – North Europe**

Tel 44 (0) 1388 770222  
Fax 44 (0) 1388 770288

#### **ASC - South Europe**

Tel 33 (0) 235 53 43 71  
Fax 33 (0) 235 53 54 44

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

**Desoclean and DeSoto are trademarks of PRC-DeSoto International, Inc.**

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PPG Aerospace  
Sealants and Coatings  
Darlington Road  
Shildon, Co Durham UK  
DL4 2QP  
[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 07/14  
Lit: 4256