

TEROSON PU 9500 FOAM

April 2015

PRODUCT DESCRIPTION

TEROSON PU 9500 FOAM provides the following characteristics:

Technology	2-part cavity-filling and sound -deadening foam
Base	Polyurethane

TEROSON PU 9500 FOAM is a ready-to-use, expanding cavity-filling and sounddeadening foam supplied in an aerosol can.

Due to its extended skin-formation time, foaming can be interrupted briefly for up to 5 minutes during application and then resumed. The foam cures without the need of moisture and is thus suitable for filling cavities. The cured foam does not subsequently swell or shrink.

Application Areas:

TEROSON PU 9500 FOAM is particularly suitable for filling and sealing cavities such as those of A-, B- and C-pillars, door sills or frame components in general. Because of its extended skin-formation time, it can be used for bonding and sealing several components, e.g. customizing. The product is employed above all in small-series production and in the repair and servicing sector (vehicle repair & maintenance sector).

TECHNICAL DATA

(Typical Test Results)

Mixing	shake about 20 times
Colour:	silver grey
Starting time	approx. 5 s
Expansion volume	up to 100 %
Yield, freely foamed	approx. 4 to 5 liters*
Density, freely foamed	approx. 35 kg/m ³
Tack-free-time	15 to 17 min*
Cuttable	after >25 min.*
Cell structure	approx 85% closed cells
Compression resistance after 24 h	20 N/cm ²
Tensile strength after 1h	6 N/cm ²
after 24h	17 N/cm ²
Shear strength after 24h	7 N/cm ²
Water absorption	
Cut	1.5 vol%
Uncut	0.8 vol%
Dimensional stability	± 5%
Optimal application temperature	18 to 23 °C
Application temperature:	10 to 35 °C
Maximum activation temperature	35 °C
In service temperature:	-40 to 80 °C

* = 23 °C, 50 % rh

PRELIMINARY STATEMENT:

Prior to use it is necessary to read the **Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

Pretreatment

The surfaces must be clean, dry and free of dust and grease. Remove loose pieces. Ensure that the workplace is well ventilated.

General Details

The aerosol can of TEROSON PU 9500 FOAM contains two chambers. The outer chamber contains the basic foam material while the inner chamber with the activation mechanism is filled with the hardener liquid. Propellants generate the pressure necessary to force out the foam and create the pores. The product is activated by using the wire to pull out the activation lid and then shaking the can vigorously up and down (20 times). Pulling on the trigger of the plastic adapter opens a valve causing the product to be extruded at the end of the mixing tube as a prefoamed bead. One of the foam components is colored. If the silver-gray color of the extruded foam is uniform, this indicates that the two components have been mixed sufficiently well. The material is highly adhesive and expands by about 50 to 100% during curing, depending on the temperature, application and available cavity volume. The curing reaction takes place independently of air humidity. The cavity-filling foam's skin-formation time has been deliberately extended so that the foam remains workable for 15 to 20 minutes, depending on temperature, before it becomes tack-free. The chemical reaction is nearly completed after about 30 minutes. Full strength is achieved after 3 to 5 hours. Low temperatures prolong curing time while high temperatures shorten it.

Application:

1. Remove the safety catch from the activation lid.
 2. Use the wire to pull the activation lid out as far as it will go (about 11 cm as far as notch).
 3. Break off wire at the intended break point (notch) above the valve.
 4. Screw plastic adapter into valve.
 5. Shake can vigorously up and down.
 6. Apply foam with valve pointing downward.
 7. About 0.25 liters of foam is extruded per second of foaming time, for free foaming.
- After activation, always release at least some of the foam.



Use sparingly as the foam expands by about 50 to 100% without confinement and by about 100 to 200% in cavities.

Cleaning

Since TEROSON PU 9500 FOAM adheres to almost all substrates, the surroundings should be masked sufficiently with paper or sheeting.

Immediately remove fresh foam residues with TEROSON VR 10. Cured foam can only be removed mechanically.

Post-Pretreatment

The cured foam can be mechanically treated by sanding, cutting or sawing. It can also be coated, painted or bonded regarding it's resistant to common used solvents.

Storage:

Frost sensitive	yes
Recommended storage temperature	15 to 25 °C
Shelf life	12 months in original packaging

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are

believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1

