

TEROSON WT 450 AQUA

January 2018

PRODUCT DESCRIPTION

TEROSON WT 450 AQUA provides the following characteristics:

	Water-based anticorrosive agent for cavity conservation
Base	Waxes and anticorrosive additives

TEROSON WT 450 AQUA is a water-based anticorrosive agent intended primarily for cavity conservation in vehicles. The material is a thixotropic solution which can be well atomized. This leads to optimum protection even of those areas which are difficult to reach and also between narrow sheet metal tolerances. The product contains a high proportion of rust inhibitors to maximize corrosion protection. TEROSON WT 450 AQUA atomizes to a fine fog during has excellent penetration characteristics, penetrates well into the gaps to be protected (e.g. welding seams), but does not run off significantly from lower seams. The material may also be applied at temperatures starting at 15°C, but penetration is improved when product and car body have normal room temperature. After complete drying TEROSON WT 450 AQUA forms a waxy, plastic, waterrepellent film with a beige translucent colour.

Application areas:

TEROSON WT 450 AQUA is primarily used in auto repair shops for spraying cavities in motor vehicle bodies in addition to the existing cavity conservation applied to new cars, for follow-up treatment after 2-3 years and after an accident damage repair. TEROSON WT 450 AQUA can also be used as a maintenance and care product for vehicle underbodies. It protects from rust, has a brightening effect on all parts looking shabby or slightly rusty. In this case spray the underbody just lightly. TEROSON WT 450 AQUA is also fitted removable protection of bare metal or painted parts, e.g. which are subjected to corrosion due to environmental effect during transportation and storage. The application on paint gives a technical variety (e.g. powder paint, repair refinish, matt painted surface,...) of surfaces and possible interaction with the wax. It is recommended to make testing and trials before the use, to have the needed protection, seal and cleaning confirmed.

TECHNICAL DATA

(Typical Test Results)

Colour:

Odour

Density

Consistency

Solids

Sag resitance

Dripping temperature of the solids

Flow time acc. to DIN 53211

beige
characteristic odour
approx. 0.99 g/cm³
thixotropic
approx. 35 %
up to 1 mm wet
> 150°C
approx. 30 s

Temperature 20 °C

Nozzle 4 mm

Corrosion resistance no corossion

Salt spray test to DIN 50021 (35°C, 5% salt solution, 240 h, 50 µm dry film thickness)

 $\begin{array}{lll} \mbox{Application temperature} & 15\ \mbox{to}\ 30\ \mbox{°C} \\ \mbox{In service temperature} & -30\ \mbox{to}\ 100\ \mbox{°C} \\ \mbox{short exposure (up to 1h)} & 130\ \mbox{°C} \end{array}$

PRELIMINARY STATEMENT

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

Pretreatment:

The surfaces to be coated with TEROSON WT 450 AQUA have to be clean, dry and free of rust, oil, grease, dust and other contamination. Areas not to be coated should be properly covered.

Caution:

Do not spray on joints, engine, gear box, prop shaft, transmissions, exhaust components, catalytic converter and the break system. As TEROSON WT 450 AQUA is a water-based product, care should be taken to allow good air access before closing the cavities off (e.g. door trim) and assure good aeration during drying phase (depending on the cavity the drying period can last up to several days). The applied coating should be allowed to dry completely before exposing the vehicle to moisture or frost.

Application:

TEROSON WT 450 AQUA is applied with the Henkel UBC-Gun from 1-l-cans. Recommended application pressure is 5-6 bar. Shake the can well before use. Fine surface structures can be obtained with the spray gun.



Cleaning:

Equipment and contaminated parts should be cleaned with water immediately after use, if necessary also use an aqueous detergent. Pure solvent based cleaners can't be used for cleaning (coagulation). Parts that have been sprayed with TEROSON WT 450 AQUA for protection during transport can be dewaxed by first spraying with a cold cleaner to soften the product, then cleaned with a steam jet.

Storage:

Frost sensitive	yes
Recommended	15 to 25 °C
storage temperature	
Shelf life	18 months

Classification:

Please refer to the corresponding **Material Safety Data Sheets** for details on:

Hazards identification Transport information Regulatory information

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 0.0